

TDS for PT-170 (Monofilament)

Division	Unit	Content	Note
Composition	%	g.bead 60 : pet 40	Embroidery, Textile
Size	mm	0.07	
Weightwise thickness	Denier	150	
Tenacity	cN	360	
Elongation	%	24	
Weight/ 10,000m	g	170	

**polyester**

TDS for PT-250 (Monofilament)

Division	Unit	Content	Note
Composition	%	g.bead 60 : pet 40	Embroidery, Textile
Size	mm	0.1	
Weightwise thickness	Denier	220	
Tenacity	cN	380	
Elongation	%	26	
Weight/ 10,000m	g	250	

**polyester**

TDS for PT-500 (Monofilament)

Division	Unit	Content	Note
Composition	%	g.bead 60 : pet 40	Sewing, Weaving
Weightwise thickness	mm	0.14	
Size	Denier	450	
Tenacity	cN	600	
Elongation	%	26	
Weight/ 10,000m	g	500	

**polyester**

TDS for PT-800 (Monofilament)

Division	Unit	Content	Note
Composition	%	g.bead 60 : pet 40	Sewing, Weaving
Weightwise thickness	mm	0.18	
Size	Denier	720	
Tenacity	cN	1,200	
Elongation	%	26	
Weight/ 10,000m	g	800	

**polyester**

TDS for BB-40S (Twisted)

Division	Unit	Content	Note
Composition	%	poly 86 : ny 14	Knit, Tricot
Twisted with		Ny 40d / 12F	
Weightwise thickness	Denier	260	
Size	mm	0.11	
Tenacity	cN	400	
Elongation	%	24	
Weight/ 10,000m	g	300	

TDS for BB-300d (Twisted)

Division	Unit	Content	Note
Composition	%	poly 100	Knit, Tricot
Twisted with		Poly300d/pt-250x2line	
Weightwise thickness	Denier	1100	
Size	mm	0.3	
Tenacity	cN	1,000	
Elongation	%	24	
Weight/ 10,000m	g	1000	